



RS
Motorbike
Paint
LTD

SPECIALISTS IN ORIGINAL MOTORBIKE COLOURS

RS Motorbike Paint Limited
Unit 5 Alpha Business Park, Welham Green,
Hertfordshire AL9 7NT
Tel / Fax: 01707 273219
Web: www.rsbikepaint.co.uk
Email: sales@rsbikepaint.co.uk
(VAT Reg. No. 364 1483 53)

Aerosol and Touch up Matt/Satin Lacquer

Description

Two component acrylic lacquer which can be applied over most suitably prepared basepaints. Any gloss surfaces must be lightly rubbed down with 1200 before application. Easy application, fast drying, non yellowing, easy to polish.

Drying Times (air drying at 20°C)

Number of coats: 2 – 3

Dust free 3 – 5 mins

Tack free 15-20 mins

Through drying: 6 hours

Interval between coats: 10 mins

Polishing: after 24 hours at room temperature. The complete hardening occurs in the following 3-4 days.

OBSERVATIONS

In case of drying at temperatures below 60°C, the painted substrate must not be exposed to severe conditions in the first days after the painting. Until the film has reached the complete cross-linking, strong humidity condensations, like dew and frost and contact with aggressive agents like smog, detergents, salt on the roads, must be avoided.